

CHILL CLEAR™

Ultra-versatile
flood coat epoxy
resin

MIXING RATIO

2:1

CHARACTERISTICS

Self leveling

Excellent UV resistance

Low viscosity

Glossy finish

Heat & impact resistance



Contact

POLYMÈRES TECHNOLOGIES

for more information:

support@polymerestechologies.com

DESCRIPTION

CHILL CLEAR™ is a 100% reactive, crystal clear, optical quality, self-leveling epoxy resin with excellent UV resistance. Its low viscosity and medium curing time make it the most versatile product in the CHILL EPOXY™ line.

CHILL CLEAR™ can be applied in thin layers or cast at a thickness of up to 0.5 inches (13 mm). It can be used to create small objects such as coasters, to fill in cracks or wood engravings, as a topcoat on canvas, countertops, and bars, or as a seal coat/flood coat on tables. It is also ideal to encapsulate small objects.

INSTRUCTIONS

PREPARATION

Before using CHILL CLEAR™, shake well each container of part A and B. Mix 2 volumes of part A with 1 volume of part B (or 100 A for 42 B by weight). Mix slowly and evenly with a metal spatula for 5 to 8 minutes making sure to scrape the edges and bottom of the container.

USAGE

Since the pot life of this system is only 60 minutes long at 22°C (72°F), make sure not to mix more material than what can be applied within this time frame. It is important to note that pot life will shorten in a warmer environment and will lengthen in a cooler one. Also, the more resin is mixed, the more its pot life decreases.

The remaining unused mixture might emit a lot of heat; beware of burn risks. Always test the product on a sample prior to using it on a project.

STORAGE

Store CHILL CLEAR™ on a pallet or shelf at 22°C (72°F) and at a relative humidity under 60%. A cold environment will increase the viscosity of parts A and B and a warm environment will decrease it. Uncured material can be easily cleaned with isopropyl alcohol or with POLYCLEANER™.



Fast setting epoxy
Pot life of 60 minutes

A/B kits available in 1.5L, 3L, 12L and 30L sizes

CHILL
EPOXY™
By Polymères Technologies

Ultra-versatile
flood coat epoxy
resin

MIXING RATIO
2:1

CHARACTERISTICS

Self leveling

Excellent UV resistance

Low viscosity

Glossy finish

Heat & impact resistance



Contact

POLYMÈRES TECHNOLOGIES

for more information:

support@polymerestechologies.com

TYPICAL PROPERTIES (AT 22 °C/72 °F)	PART A	PART B	MIX
VISCOSITY (Brookfield (cps))	725	195	225
CONSISTENCY	Liquid		
DENSITY (g/cm ³)	1.14	1.00	1.09
MIXING RATIO IN VOLUME	2	1	2/1
MIXING RATIO IN WEIGHT	100	42	100/42
COLOR	Transparent		
POT LIFE for 200g	60 minutes		
DEMOLDING TIME	7 days depending on the mass		
PEAK EXOTHERMIC TEMPERATURE (ASTM D 2471-71)	168 °C		
FULL CURE*	3 days depending on piece design and volume		

*After material has solidified, the curing process can be accelerated at 51.7°C (125°F).

PHYSICAL PROPERTIES (SOLID STATE AFTER 7 DAYS AT 22 °C/72 °F)

TEST	METHOD	RESULTS	
HARDNESS	ASTM D 785 65	Shore D	83
COMPRESSIVE STRENGTH	ASTM D 695 80	MPa*	91.62
		Maximum strain %	3.9
TENSILE STRENGTH	ASTM D 638 Type 1	MPa	46
FLEXURAL STRENGTH	ASTM D 790A	MPa	119
ELONGATION	ASTM D 790A	%	4.1
DEFLECTION TEMPERATURE		455 kPa**	52 °C
		1820 kPa	54 °C
IMPACT RESISTANCE	ASTM D 256 81	J/m***	77
LINEAR SHRINKAGE	ASTM D 2566 79	cm/cm	0.0021
ABRASION RESISTANCE	TABER CS 17-1000 GR	0.068	
COEFFICIENT OF LINEAR THERMAL EXPANSION	ASTM D 696 79	4.135 x 10 ⁻⁵	

*1 MPa = 145 lb
**1 kPa = 0.145 psi
***53.4 J/m = 1 blF/po

PRECAUTIONS

- Consult material safety data sheet prior to use.
- Normal health and safety measures should be observed when handling this product.
- Ensure good ventilation.
- Wear gloves, safety glasses, and protective clothing.
- Once the container is opened, POLYMÈRES TECHNOLOGIES can no longer be held responsible for this product.
- Shelf life of this product in original containers is one (1) year from the date of purchase, under recommended storage conditions.

IMPORTANT:

Part B of this system tends to oxidize if exposed to ambient air. Quickly close the container after use and avoid leaving it in the open for a long period. Keep the containers at a temperature of 22 °C (72 °C) and with a relative humidity of less than 60%.

The oxidation of part B does not affect the performance of the product in any way. The addition of a color pigment will mask the yellowing.

To control this situation, we package our products under nitrogen atmosphere in premium quality metal containers instead of HDPE plastic containers, the latter allowing the product to breathe and get contaminated.

It is important to test the color of the hardener mixed with part A before doing any project. In the event that the obtained color is unsatisfying, the customer should purchase a new kit, as both parts A and B are not usually sold individually.

It is recommended to follow provincial and federal safety regulations. In case of eye contact, rinse well with water. In case of skin contact, rinse with soap and water. Keep away from children.

GUARANTEE

Having no control over the use and application of this product, the manufacturer and/or distributor cannot guarantee the result obtained. The warranty is therefore limited to the replacement of a product that the user has demonstrated to the satisfaction of the manufacturer and distributor that it is actually defective. Before using this product, the user must ensure that the product is suitable for its intended use. Only the user assumes the risks related to this use. The user must ensure that this product meets his needs by conducting tests in the short, medium and long term to validate the results and in the conditions of use and according to the instructions provided. This limited warranty excludes all liability for consequential, incidental or special damages. Except as described above, the user expressly acknowledges and accepts at the time of the purchase of this product that the manufacturer and / or distributor disclaims any other liability and any other express or implied warranty of quality and an implied warranty of quality of the material are expressly excluded.

sales@polymerestechologies.com

6330 Boulevard Laurier O, Saint-Hyacinthe, QC J2S 9A7

+1 (450) 250-3058