TECHNICAL SHEET

CHILL 3D™

Ideal for the protection of different substrates

> MIXING RATIO **1A:1B** by volume

CHARACTERISTICS

Doming effect

Protects and improves substrates

Medium viscosity

Excellent UV resistance

Glossy finish



for more information: support@polymerestechnologies.com

DESCRIPTION

CHILL 3DTM is a 100% reactive, VOC-free, highly UV-resistant topcoat epoxy system. Its medium viscosity, unique in the CHILL EPOXYTM line, minimizes dripping and gives better control on the fusion of colors and pigments during casting.

This product can be applied to almost any surface or material that is free of grease or contaminants. Ideal for clear or pigmented finishing coats on various surfaces to enhance and magnify their appearance.

INSTRUCTIONS

PREPARATION

Before using CHILL $3D^{TM}$, mix 1 volume of part A with 1 volume of part B (or 100 A for 85 B by weight). Mix slowly and evenly with a metal spatula for 5 to 8 minutes making sure to scrape the edges and bottom of the container.

USAGE

Since the pot life of this system is only 60 minutes long at $22^{\circ}C$ ($72^{\circ}F$), make sure not to mix more material than what can be applied within this time frame. It is important to note that pot life will shorten in a warmer environment and will lengthen in a cooler one. Also, the more resin is mixed, the more its pot life decreases.

The remaining unused mixture might emit a lot of heat; beware of burn risks. Always test the product on a sample prior to using it on a project.

STORAGE

Store CHILL $3D^{TM}$ on a pallet or shelf at $22^{\circ}C$ ($72^{\circ}F$) with relative humidity under 60%. A cold environment will increase the viscosity of parts A and B and a warm environment will decrease it. Uncured material can be easily cleaned with isopropyl alcohol or with POLY CLEANERTM.

CNUL 33	1 (2000
Martin H.	and the state
Contraction of the second	CHILL
the start and	200000000 00000000000000000000000000000
Sal Income	그녀님님. 🍖 🎦 이네
Witt of a farmer of the state	2000 N 2 1 1
Call State of the	
Support and the second	100. O
NER THE TREAMENT	FRANK EPOXY SYSTEMS
Supervise of the second	PRESITO
Street and the local diversion of	COUCHE DE FINITION ET CANEVAS
and a state of the state of the state	POUR COMPTONES
and the second second	CODXY TOPCOAT FOR
States and a state of the state	COUNTERTOPS AND CANVA
Sec. State	DONING EFFECT
and the Car	EFFET DE DUHE PROTECTS AND
Contraction of the	PROTECE ET EMPERATS INPROVES SOUTH
nu the	WWINNE VISCOBILE NEDIDA VISCOBILE
10 10 10 10 10 10 10 10 10 10 10 10 10 1	DICFULINTE RESISTANCE
The states and	MESISTANCE AND A GLOSEY FINISH
A CONTRACT	O management
The new Construction of the ne	0 10 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1
and they were they	60 0 0
and the state of t	AN A COM
The second interest	
and and a second second	10 - Contraction
2 3	
the way and	CAUTION
June the Court	ATTENTION CAUTION
	FRANK PARTY AND

Fast setting epoxy Pot life of 60 minutes

A/B kits available in 1L, 2L and 8L sizes



CHILL 3D™

Ideal for the protection of different substrates

> MIXING RATIO **1A:1B** by volume





POLYMÈRES TECHNOLOGIES for more information: support@polymerestechnologies.com

TYPICAL PROPERTIES (AT 22 °C/72 °F)	PART A	PART B	ΜΙΧ	
VISCOSITY (Brookfield (cps))	3600	3400	3500	
CONSISTENCY	Liquid			
DENSITY (g/cm ³)	1.169	1.034	1.102	
MIXING RATIO IN VOLUME	1	1	1/1	
MIXING RATIO IN WEIGHT	100	85	100/85	
COLOR	Transparent			
POT LIFE for 200g	60 minutes			
DEMOLDING TIME	7 days depending on the mass			
PEAK EXOTHERMIC TEMPERATURE (ASTM D 2471-71)	161 °C			
FULL CURE*	2 to 3 days depending on piece design and volume			
*After material has solidified, the curing process can be accelerated at 51.7°C (125°F).				

TECHNICAL SHEET

PHYSICAL PROPERTIES (SOLID STATE AFTER 7 DAYS AT 22 °C/72 °F)

TEST	METHOD	RESULTS	
HARDNESS	ASTM D 785 65	Shore D	82
COMPRESSIVE STRENGTH	ASTM D 695 80	MPa*	89.54
		Maximum strain %	4.6
TENSILE STRENGTH	ASTM D 638 Type 1	MPa	47
FLEXURAL STRENGTH	ASTM D 790A	MPa	122
ELONGATION	ASTM D 790A	%	4.4
DEFLECTION TEMPERATURE		455 kPa**	56 °C
		1820 kPa	54 °C
IMPACT RESISTANCE	ASTM D 256 81	J/m***	4
LINEAR SHRINKAGE	ASTM D 2566 79	cm/cm	0.00021
ABRASION RESISTANCE	TABER CS 17-1000 GR	0.059	
COEFFICIENT OF LINEAR THERMAL EXPANSION	ASTM D 696 79	4.12 x 10 ⁻⁵	
*1 MPa = 145 lb **1 kPa = 0.145 psi ***53.4 J/m = 1 blF/po			



PRECAUTIONS

- Consult material safety data sheet prior to use.
- Normal health and safety measures should be observed when handling this product.
- Ensure good ventilation.
- Wear gloves, safety glasses, and protective clothing.
- Do not use part A without its part B, and vice versa. Shake well parts A and B separately before use.
- Once the container is opened, POLYMÈRES TECHNOLOGIES can no longer be held responsible for this product.
- Shelf life of this product in original containers is one (1) year from the date of purchase, under recommended storage conditions.
- Keep from freezing.

IMPORTANT:

Part B of this system tends to oxidize if exposed to ambient air. Quickly close the container after use and avoid leaving it in the open for a long period. Keep the containers at a temperature of 22 $^{\circ}$ C (72 $^{\circ}$ C) and with a relative humidity of less than 60%.

The oxidation of part B does not affect the performance of the product in any way. The addition of a color pigment will mask the yellowing.

To control this situation, we package our products under nitrogen atmosphere in premium quality metal containers instead of HDPE plastic containers, the latter allowing the product to breathe and get contaminated.

It is important to test the color of the hardener mixed with part A before doing any project. In the event that the obtained color is unsatisfying, the customer should purchase a new kit, as both parts A and B are not usually sold individually.

It is recommended to follow provincial and federal safety regulations. In case of eye contact, rinse well with water. In case of skin contact, rinse with soap and water. Keep away from children.

ASSUMPTION OF RISK

The customer assumes all risk and liability for the results obtained by the use of any POLYMÈRES TECHNOLOGIES product, including, without limiting the generality of the foregoing, the use of the CHILL EPOXY[™] line of products, and the use of any process, whether in terms of general effectiveness, success, or failure, and regardless of any oral or written statement made by way of technical advice or otherwise, related to the use of any POLYMÈRES TECHNOLOGIES product.

sales@polymerestechnologies.com 6330 Boulevard Laurier O, Saint-Hyacinthe, QC J2S 9A7 +1 (450) 250-3058

