

CHILL ICE™ 1

TECHNICAL SHEET

1

For small to medium-sized castings
(0.5 to 1.5" thick)

MIXING RATIO
2A : 1B
by volume

CHARACTERISTICS

Easy degassing

Excellent UV resistance

Slow setting time

Glossy finish

No fans or blowtorch required



Contact

POLYMÈRES TECHNOLOGIES

for more information:

support@polymerestechnologies.com

DESCRIPTION

CHILL ICE™ 1 is a 100% reactive, VOC-free, crystal clear, optical quality casting system with low viscosity and high ultraviolet resistance. Its slow setting time ensures a controlled exothermic reaction, thus reducing the risks of shrinkage, cracking, and premature yellowing.

This product allows the mixing of several liters at a time to be poured up to 1.5" thick (38 mm) in a single casting. Ideal for medium-sized projects such as charcuterie boards, small river tables, deep cracks, and more. Also available in kits of 12, 30, and 60L for larger projects.

INSTRUCTIONS

PREPARATION

Before using CHILL ICE™ 1, mix 2 volumes of part A with 1 volume of part B (or 100 A for 42 B by weight). Mix slowly and evenly with a metal spatula for 5 to 8 minutes while making sure to scrape the edges and bottom of the container.

USAGE

As the pot life of this system is 500 minutes at 22°C (72°F) for a mass of 200g, it is possible to mix many liters at once and pour a large quantity of resin. It is important to note that pot life will shorten in a warmer environment and will lengthen in a cooler one. Also, the more resin is mixed, the more its pot life decreases.

The remaining unused mixture might emit a lot of heat; beware of burn risks. Always test the product on a sample prior to using it on a project.

STORAGE

Store CHILL ICE™ 1 on a pallet or shelf at 22°C (72°F) and at a relative humidity under 60%. A cold environment will increase the viscosity of parts A and B and a warm environment will decrease it. Uncured material can be easily cleaned with isopropyl alcohol or with POLY CLEANER™.



Slow setting epoxy
Pot life of 500 minutes

A/B kits available in 1.5L, 3L, 12L,
30L and 60L sizes

CHILL
EPOXY™
By Polymères Technologies

CHILL ICE™ 1

For small to medium-
sized castings
(0.5 to 1.5" thick)

MIXING RATIO
2A : 1B
by volume

CHARACTERISTICS

Easy degassing

Excellent UV resistance

Slow setting time

Glossy finish

No fans or blowtorch required

TEMPS DE VIE EN POT / POT LIFE
500
MIN

JUSQU'À / UP TO
1 1/2"
38 MM

SANS COV / VOC FREE
0%

Contact

POLYMÈRES TECHNOLOGIES

for more information:

support@polymerestechologies.com

TECHNICAL SHEET

2

TYPICAL PROPERTIES (AT 22 °C/72 °F)	PART A	PART B	MIX
VISCOSITY (Brookfield (cps))	725	50	195
CONSISTENCY	Liquid		
DENSITY (g/cm³)	1.08	0.95	1.03
MIXING RATIO IN VOLUME	2	1	2/1
MIXING RATIO IN WEIGHT	100	42	100/42
COLOR	Transparent		
POT LIFE for 200g	500 minutes		
DEMOLDING TIME	7 days depending on the mass		
PEAK EXOTHERMIC TEMPERATURE (ASTM D 2471-71)	86 °C		
FULL CURE*	7 days depending on piece design and volume		
*After material has solidified, the curing process can be accelerated at 51.7°C (125°F).			

PHYSICAL PROPERTIES (SOLID STATE AFTER 7 DAYS AT 22 °C/72 °F)

TEST	METHOD	RESULTS	
HARDNESS	ASTM D 785 65	Shore D	81
COMPRESSIVE STRENGTH	ASTM D 695 80	MPa*	88.34
		Maximum strain %	4.2
TENSILE STRENGTH	ASTM D 638 Type 1	MPa	45
FLEXURAL STRENGTH	ASTM D 790A	MPa	120
ELONGATION	ASTM D 790A	%	4.9
DEFLECTION TEMPERATURE		455 kPa**	52 °C
		1820 kPa	46 °C
IMPACT RESISTANCE	ASTM D 256 81	J/m***	76
LINEAR SHRINKAGE	ASTM D 2566 79	cm/cm	0.0026
ABRASION RESISTANCE	TABER CS 17-1000 GR	0.060	
COEFFICIENT OF LINEAR THERMAL EXPANSION	ASTM D 696 79	4.085 x 10 ⁻⁵	
*1 MPa = 145 lb **1 kPa = 0.145 psi ***53.4 J/m = 1 blF/po			

TAKE NOTICE

IF CHILL ICE™ 1 IS POURED
BELOW RECOMMENDATIONS
AND/OR IN A SMALLER MASS, THE
FULL CURE TIME CAN DOUBLE.

CHILL
EPOXY™
By Polymères Technologies

PRECAUTIONS

- Consult material safety data sheet prior to use.
- Normal health and safety measures should be observed when handling this product.
- Ensure good ventilation.
- Wear gloves, safety glasses, and protective clothing.
- Do not use part A without its part B, and vice versa. Shake well parts A and B separately before use.
- Once the container is opened, POLYMÈRES TECHNOLOGIES can no longer be held responsible for this product.
- Shelf life of this product in original containers is one (1) year from the date of purchase, under recommended storage conditions.
- Keep from freezing.

IMPORTANT:

As is the case with all epoxy products, part B of this system tends to oxidize with time. This is a reaction of oxygen with air causing a slow discoloration of part B. Heat and high relative humidity will intensify this reaction. Oxidation starts as soon as the container of part B has been opened.

The oxidation of part B does not affect the performance of the product in any way. The addition of a color pigment will mask the yellowing.

To control this situation, we package our products under nitrogen atmosphere in premium quality metal containers instead of HDPE plastic containers, the latter allowing the product to breathe and get contaminated.

It is important to test the color of the hardener mixed with part A before doing any project. In the event that the obtained color is unsatisfying, the customer should purchase a new kit, as both parts A and B are not usually sold individually.

It is recommended to follow provincial and federal safety regulations. In case of eye contact, rinse well with water. In case of skin contact, rinse with soap and water. Keep away from children.

ASSUMPTION OF RISK

The customer assumes all risk and liability for the results obtained by the use of any POLYMÈRES TECHNOLOGIES product, including, without limiting the generality of the foregoing, the use of the CHILL EPOXY™ line of products, and the use of any process, whether in terms of general effectiveness, success, or failure, and regardless of any oral or written statement made by way of technical advice or otherwise, related to the use of any POLYMÈRES TECHNOLOGIES product.

sales@polymerestechnologies.com

6330 Boulevard Laurier O, Saint-Hyacinthe, QC J2S 9A7

+1 (450) 250-3058



CHILL
EPOXY™
By Polymères Technologies